



CROSSLINK TECHNOLOGY INC.

FORMULATED EPOXIES, URETHANES - CUSTOM CAST PARTS



TECHNICAL BULLETIN: CLR 1476 / CLH 6730

PRODUCT DESCRIPTION:

A LOW VISCOSITY, GENERAL PURPOSE, ROOM TEMPERATURE CURING, EPOXY ENCAPSULANT. PRODUCT IS FILLED WITH NON-ABRASIVE FILLERS SUITABLE FOR MACHINE DISPENSING. PRODUCT HAS GOOD PHYSICAL, THERMAL AND ELECTRICAL PROPERTIES.

SALES SPECIFICATION	CLR 1476	CLH 6730
COLOUR	BLACK	AMBER
VISCOSITY (NOTE 1, NOTE 4)	30000 - 50000 CPS	60 - 100 CPS
SPECIFIC GRAVITY	1.61 ± 0.03 gm/cm ³	1.00 ± 0.02 gm/cm ³
SHELF LIFE	12 MONTHS	12 MONTHS

HANDLING:

MIX RATIO BY WEIGHT (A:B) (NOTE 2)	100:7 (by vol. 100:12.0)
MIXED VISCOSITY (NOTE 4)	12000 cps @ 22 °C
POT LIFE OF 200 gm. mass (NOTE 4)	45.00 Min. @ 22 °C
GEL TIME OF 200 gm. mass (NOTE 4)	50.00 Min. @ 22 °C

GEL TIME 10 gm. mass~92 min. @ 22c.

CURE SCHEDULE (NOTE 3):

RECOMMENDED CURE SCHEDULE	24 Hrs. @ 22 °C
ALTERNATE CURE SCHEDULE	4 Hrs. @ 60 °C

CURED PROPERTIES: (NOT INTENDED FOR PREPARATION OF SPECIFICATIONS)

COLOUR	BLACK
DENSITY (gm/cm ³)	1.58
SHORE HARDNESS	87D
TENSILE STRENGTH (psi) (ASTM D 638)	6500
TENSILE ELONGATION (%) (ASTM D 638)	4.0
FLEXURAL STRENGTH (psi)	10000
LINEAR SHRINKAGE (in/in) (ASTM D 2566)	0.0010

ELECTRICAL PROPERTIES

DIELECTRIC CONSTANT	@1 MHz	4.40
DISSIPATION FACTOR A	@1 MHz	0.0400
DIELECTRIC STRENGTH	450 Volts/Mil	62.5 Mil/Section
VOLUME RESISTIVITY		50 x10 ¹⁴

NOTES

Note1 If a filled resin, settling may occur during transportation or storage. Fillers must be remixed before use.

Note2 Mix ratio must be within $\pm 2\%$ of the stated amount and thorough mixing is required to avoid degraded final properties.

Note3 Other cure schedules may give satisfactory results, however, these should be determined by the customer for their given circumstances.

Note4 All measurements taken at 22°C unless otherwise specified.

Note5 These products may trigger allergic responses in some individuals. Prevent contact with skin, wash with plenty of soap and water immediately if contact occurs. Do not breathe vapours, provide good ventilation and exercise good housekeeping at work area. Read the Material Safety Data Sheet.

Note6 The "Guide to Operating Temperature" is based on our experience with materials of similar chemistry and/or thermal index. The ultimate suitability of this product for a given operating temperature is application dependent and may change according to the demands placed upon it in operation.

Note7 If indicated, the values under "Electrical Characteristics" may be based on supplier data for products with similar compositions. They are provided only as a guide and the recipient must test each material to determine its suitability for the intended application.

IMPORTANT

THE INFORMATION IN THIS BULLETIN IS BASED ON DATA OBTAINED BY OUR OWN RESEARCH AND IS CONSIDERED ACCURATE. ALL INFORMATION SUPPLIED BY CROSSLINK TECHNOLOGY INC., IS FURNISHED UPON THE EXPRESS CONDITION THAT THE PERSON RECEIVING THE PRODUCT SHALL MAKE THEIR OWN ASSESSMENTS TO DETERMINE ITS SUITABILITY FOR THEIR PARTICULAR PURPOSE. NO WARRANTY IS EXPRESSED OR IMPLIED REGARDING SUCH INFORMATION, OR THE RESULTS TO BE OBTAINED FROM THE USE THEREOF; THAT ANY PRODUCT SHALL BE MERCHANTABLE OR FIT FOR ANY PARTICULAR PURPOSE; OR THAT THE USE OF SUCH OTHER INFORMATION OR PRODUCT WILL NOT INFRINGE ANY PATENT.

